



תכונות הקפיציות לסוגים D / E



* תכונות דחיסה				D / H (mm)	* תכונות דחיסה				D / H (mm)
Compression Characteristics					Compression Characteristics				
Load (N) מאמץ			Deflection דחיסה (mm)		Load (N) מאמץ			Deflection דחיסה (mm)	
68°	57°	43°			68°	57°	43°		
400.0	273.0	152.0	1.8	40/40	22.1	15.9	8.3	0.4	10/10
801.0	546.0	303.0	3.6		167.0	115.0	83.0	0.9	
1,201.0	818.0	454.0	5.4		805.0	553.0	308.0	1.3	
980.0	678.0	374.0	1.0	50/20	64.0	43.7	23.7	0.6	15/15
1,861.0	1,289.0	711.0	1.9		128.0	87.5	47.5	1.2	
2,841.0	1,967.0	1,086.0	2.9		181.0	124.0	67.3	1.7	
805.0	553.0	308.0	1.3	50/30	127.0	84.1	46.2	0.6	20/15
1,548.0	1,064.0	592.0	2.5		254.0	168.0	92.3	1.2	
2,352.0	1,617.0	900.0	3.8		360.0	238.0	130.8	1.7	
641.0	443.0	243.0	2.0	50/40	98.0	66.7	40.0	0.8	20/20
1,282.0	887.0	487.0	4.0		333.0	231.0	166.0	1.8	
1,922.0	1,330.0	730.0	6.0		500.0	346.0	249.0	2.7	
613.0	399.0	237.0	2.3	50/50	167.0	115.0	83.0	0.9	25/20
1,227.0	797.0	473.0	4.6		347.6	244.2	151.8	1.6	
1,840.0	1,196.0	710.0	6.9		521.4	366.3	226.6	2.4	
1,393.0	1,014.0	540.0	2.0	70/40	261.0	180.0	99.5	0.9	30/20
2,717.0	1,977.0	1,054.0	3.9		522.0	359.0	199.0	1.8	
4,110.0	2,991.0	1,594.0	5.9		783.0	539.0	298.0	2.7	
2,034.0	1,403.0	789.0	1.7	75/40	248.0	157.0	83.3	1.3	30/30
3,948.0	2,724.0	1,531.0	3.3		496.0	314.0	167.0	2.6	
5,982.0	4,127.0	2,319.0	5.0		744.0	471.0	250.0	3.9	
1,592.0	1,100.0	610.0	2.4	75/50	451.0	309.0	171.0	1.3	40/30
3,185.0	2,200.0	1,221.0	4.8		902.0	617.0	342.0	2.6	
4,777.0	3,300.0	1,831.0	7.2		1,353.0	926.0	512.0	3.9	

* יתכן סטייה של עד 20% בערכים המצוינים עקב טולרנסים ביצור וקשיות.

תכונות הקפיציות לסוגים D / E



* תכונות דחיסה *				D / H (mm)	* תכונות דחיסה *				D / H (mm)
Compression Characteristics					Compression Characteristics				
Load (N) מאמץ			Deflection דחיסה (mm)		Load (N) מאמץ			Deflection דחיסה (mm)	
68°	57°	43°			68°	57°	43°		
3,318.7	2,302.3	1,255.1	2.6	100/60	1,677.9	1,152.9	640.5	2.5	75/55
6,638.5	4,603.5	2,510.2	5.2		3,288.6	2,259.6	1,254.8	4.9	
9,957.2	6,905.8	3,764.2	7.8		4,966.5	3,412.5	1,894.2	7.4	
2,800.0	1,939.0	1,044.0	3.4	100/75	4,070.0	2,851.0	1,577.0	1.8	100/40
5,518.0	3,821.0	2,058.0	6.7		8,140.0	5,702.0	3,154.0	3.6	
8,319.0	5,761.0	3,102.0	10.1		12,210.0	8,552.0	4,730.0	5.4	
2,456.0	1,699.0	943.0	4.8	100/100	3,277.0	2,203.0	1,240.0	2.3	100/50
4,913.0	3,397.0	1,886.0	9.6		6,555.0	4,406.0	2,480.0	4.6	
7,369.0	5,096.0	2,829.0	14.4		9,832.0	6,609.0	3,720.0	6.9	
7,750.1	4,298.7	2,976.8	3.3	150/75	3,840.0	2,721.6	1,527.6	2.4	100/55
15,500.1	8,599.5	5,954.6	6.6		7,520.4	5,329.2	2,990.4	4.7	
23,249.1	12,899.3	8,931.3	9.9		11,360.4	8,050.8	4,518.0	7.1	
13,090.0	9,214.0	5,031.0	4.5	200/100					
26,180.0	18,428.0	10,026.0	9.0						
39,270.0	27,642.0	15,093.0	13.5						

* יתכן סטייה של עד 20% בערכים המצוינים עקב טולרנסים ביצור וקשיות.

