



תכונות הקפיציות לסוג C



* תכונות תזוזה				* תכונות דחיסה				D / H (mm)
Shear Characteristics				Compression Characteristics				
Load (N) מאמץ			Deflection תזוזה (mm)	Load (N) מאמץ			Deflection דחיסה (mm)	
68°	57°	43°		68°	57°	43°		
6.6	4.6	2.5	0.6	17.7	12.1	4.3	0.3	8/8
13.2	9.1	5.0	1.2	35.4	24.1	8.5	0.6	
19.8	13.7	7.6	1.8	53.0	36.2	12.8	0.9	
10.8	7.4	4.2	0.7	25.9	17.9	8.9	0.4	10/10
21.6	14.9	8.3	1.4	45.4	31.4	15.5	0.7	
32.4	22.3	12.5	2.1	71.4	49.3	24.4	1.1	
25.4	17.6	9.8	1.2	64.6	39.7	18.6	0.6	15/15
50.8	35.2	19.6	2.4	128.7	79.4	37.2	1.2	
76.1	52.9	29.4	3.6	193.6	118.8	55.7	1.8	
40.2	26.1	14.4	1.1	113.0	78.3	50.0	0.6	20/15
80.5	52.1	28.9	2.2	206.0	144.0	91.7	1.1	
121.0	78.2	43.3	3.3	319.0	222.0	142.0	1.7	
38.7	26.7	14.8	1.6	98.0	66.7	40.0	0.8	20/20
77.3	53.3	29.7	3.2	196.0	133.0	80.0	1.6	
116.0	80.0	44.5	4.8	294.0	200.0	120.0	2.4	
70.4	49.2	25.4	1.6	173.8	122.1	75.6	0.8	25/20
140.8	98.3	50.9	3.2	347.6	244.2	151.8	1.6	
211.2	147.4	76.3	4.8	521.4	366.3	226.6	2.4	
115.3	79.8	44.4	1.6	298.8	205.0	133.8	0.8	30/20
230.0	160.0	88.8	3.2	596.3	408.8	267.5	1.6	
346.3	238.8	133.8	4.8	893.8	613.8	401.3	2.4	
101.5	70.2	38.9	2.6	222.2	154.0	87.9	1.3	30/30
203.5	140.8	77.9	5.2	444.4	308.0	176.0	2.6	
304.7	210.1	116.6	7.8	667.7	462.0	264.0	3.9	

* יתכן סטייה של עד 20% בערכים המצוינים עקב טולרנסים ביצור וקשיות.


תכונות הקפיציות לסוג C



* תכונות תזוזה				* תכונות דחיסה				D / H (mm)
Shear Characteristics				Compression Characteristics				
Load (N) מאמץ			Deflection תזוזה (mm)	Load (N) מאמץ			Deflection דחיסה (mm)	
68°	57°	43°		68°	57°	43°		
180.4	124.3	64.6	2.6	433.4	275.0	187.0	1.3	40/30
360.8	248.6	128.7	5.2	866.8	550.0	375.1	2.6	
541.2	374.0	193.6	7.8	1,300.2	823.9	562.1	3.9	
172.2	118.7	66.0	3.6	370.7	256.2	159.6	1.8	40/40
343.4	237.3	132.3	7.2	740.3	511.4	319.2	3.6	
515.6	357.0	198.5	10.8	1,110.9	767.6	478.8	5.4	
257.0	177.0	99.0	1.6	1,289.0	800.0	432.0	0.8	50/20
513.0	354.0	197.0	3.2	2,578.0	1,600.0	865.0	1.6	
770.0	531.0	296.0	4.8	3,866.0	2,400.0	1,297.0	2.4	
307.2	212.4	118.8	2.6	891.6	619.2	343.2	1.3	50/30
615.6	424.8	236.4	5.2	1,783.2	1,237.2	685.2	2.6	
922.8	637.2	355.2	7.8	2,674.8	1,856.4	1,028.4	3.9	
289.8	185.9	104.0	3.6	699.3	494.6	278.3	1.8	50/40
578.6	371.7	207.9	7.2	1,398.6	988.1	556.5	3.6	
867.3	557.6	311.9	10.8	2,097.9	1,482.6	834.8	5.4	
256.0	177.0	98.3	4.6	613.0	399.0	237.0	2.3	50/50
511.0	354.0	197.0	9.2	1,227.0	797.0	473.0	4.6	
767.0	531.0	295.0	13.8	1,840.0	1,196.0	710.0	6.9	
527.1	364.4	197.4	3.9	1,540.4	1,023.8	568.1	2.0	70/40
1,054.2	727.7	394.8	7.8	3,004.1	1,997.1	1,107.8	3.9	
1,581.3	1,092.0	591.2	11.7	4,544.4	3,021.9	1,674.8	5.9	
633.6	438.9	243.1	3.4	2,022.9	1,405.8	778.8	1.7	75/40
1,266.1	876.7	486.2	6.8	4,046.9	2,811.6	1,557.6	3.4	
1,899.7	1,315.6	730.4	10.2	6,069.8	4,218.5	2,336.4	5.1	

* יתכן סטייה של עד 20% בערכים המצוינים עקב טולרנסים ביצור וקשיות.


תכונות הקפיציות לסוג C



* תכונות תזוזה				* תכונות דחיסה				D / H (mm)
Shear Characteristics				Compression Characteristics				
Load (N) מאמץ			Deflection תזוזה (mm)	Load (N) מאמץ			Deflection דחיסה (mm)	
68°	57°	43°		68°	57°	43°		
601.7	417.9	232.1	4.4	1,698.9	1,169.7	651.0	2.2	75/50
1,202.3	835.8	464.1	8.8	3,396.8	2,340.5	1,301.0	4.4	
1,803.9	1,254.8	696.2	13.2	5,095.7	3,510.2	1,950.9	6.6	
604.8	417.9	232.1	4.9	1,677.9	1,152.9	640.5	2.5	75/55
1,208.6	835.8	464.1	9.8	3,288.6	2,259.6	1,254.8	4.9	
1,813.4	1,253.7	696.2	14.7	4,966.5	3,412.5	1,894.2	7.4	
1,023.0	708.0	393.0	3.2	4,661.0	3,127.0	1,576.0	1.6	100/40
2,047.0	1,416.0	786.0	6.4	9,322.0	6,254.0	3,153.0	3.2	
3,070.0	2,124.0	1,179.0	9.6	13,983.0	9,381.0	4,729.0	4.8	
1,280.0	715.0	491.3	4.2	4,291.3	2,975.0	1,680.0	2.1	100/50
2,560.0	1,428.8	982.5	8.4	8,583.8	5,948.8	3,361.3	4.2	
3,840.0	2,143.8	1,473.8	12.6	12,875.0	8,923.8	5,041.3	6.3	
1,011.6	849.6	471.6	4.7	3,840.0	2,721.6	1,527.6	2.4	100/55
2,023.2	1,699.2	943.2	9.4	7,520.4	5,329.2	2,990.4	4.7	
3,034.8	2,548.8	1,414.8	14.1	11,360.4	8,050.8	4,518.0	7.1	
1,125.3	778.8	432.3	5.2	3,318.7	2,302.3	1,255.1	2.6	100/60
2,250.6	1,556.5	864.6	10.4	6,638.5	4,603.5	2,510.2	5.2	
3,374.8	2,335.3	1,296.9	15.6	9,957.2	6,905.8	3,764.2	7.8	
1,022.0	708.0	393.0	6.7	2,800.0	1,939.0	1,044.0	3.4	100/75
2,045.0	1,416.0	786.0	13.4	5,518.0	3,821.0	2,058.0	6.7	
3,067.0	2,124.0	1,178.0	20.1	8,319.0	5,761.0	3,102.0	10.1	
2,415.0	1,451.1	924.0	6.6	7,750.1	4,298.7	2,976.8	3.3	150/75
4,831.1	2,902.2	1,884.8	13.2	15,500.1	8,599.5	5,954.6	6.6	
7,246.1	4,353.3	2,827.7	19.8	23,249.1	12,899.3	8,931.3	9.9	

* יתכן סטייה של עד 20% בערכים המצוינים עקב טולרנסים ביצור וקשיות.

תכונות הקפיציות לסוג C



* תכונות תזוזה				* תכונות דחיסה				D / H (mm)
Shear Characteristics				Compression Characteristics				
Load (N) מאמץ			Deflection תזוזה (mm)	Load (N) מאמץ			Deflection דחיסה (mm)	
68°	57°	43°		68°	57°	43°		
4,087.0	2,829.0	1,571.0	9.0	13,090.0	9,214.0	5,031.0	4.5	200/100
8,174.0	5,658.0	3,143.0	18.0	26,180.0	18,428.0	10,026.0	9.0	
12,261.0	8,487.0	4,714.0	27.0	39,270.0	27,642.0	15,093.0	13.5	

* יתכן סטייה של עד ±20% בערכים המצוינים עקב טולרנסים ביצור וקשיות.

